



Technical Data Sheet

Product	BCA01EAx SheenSeries										
Description	Clear polyurethane self sealers										
Color	Clear										
Woods / Substrates for which the product is suitable	Light color hardwood										
	Dark color hardwood										
Chemical-physical Properties											
CODE	Density (Kg/l)				Density (lb/US gal)				Solid content %		
BCA01EA6	0,940 ± 0,030				7,8 ± 0,3				27,1 ± 2		
BCA01EA4	0,945 ± 0,030				7,9 ± 0,3				26,2 ± 2		
BCA01EA3	0,930 ± 0,030				7,8 ± 0,3				25,5 ± 2		
	Viscosity (EN ISO 2431) ISO 5 cup					53 ±		4			
	Viscosity (DIN 53211 mm 4; 20°C - 68°F)					35 ±		3			
USAGE INDICATIONS											
Additional products					Quantities						
Hardener	BCA01HB				In weight w/w %				20		
					In volume v/v %				22,2		
	Solid content %				5,2 ±		2				
Thinner	LZC941				In weight w/w %				50		
					In volume v/v %				54		
READY TO USE PRODUCT PROPERTIES (AVERAGE)											
	Solid content 1st + 2nd component (%)				23,5 ±		2				
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)				72 h						
	Viscosity (DIN 53211 mm 4; 20°C - 68°F)				20 ±		2				
Code/Sheen	CODE				Sheen level EN ISO 2813 (angle measurement 60°)						
					applied micron: 100						
					Wet Mils: 3,9						
	BCA01EA6				Sheen		10 ±	1			
	BCA01EA4				Sheen		20 ±	2			
	BCA01EA3				Sheen		30 ±	2			



Application		Quantities			
	Airmix spray	gr/m² min-max:	80	-	100
		Wet Mils min-max	3,5	-	4,3
	Robot spray	gr/m² min-max:	80	-	100
		Wet Mils min-max	3,5	-	4,3
	Hand spray	gr/m² min-max:	80	-	100
Wet Mils min-max		3,5	-	4,3	
PRODUCT PROPERTIES AFTER APPLICATION					
Drying	Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying		1 h		
	Dust free		15 min		
	Touch dry		30 min		
	Hard dry		1 h		
	Sandable after (time)		1 h		
	Overcoatability time between layers		1 h		
			(Time and temperature according to the drying system in use)		
	Hot air drying				
Shelf life	12 months after production				
SPECIFIC WARNINGS	Pot-life time is obtained taking care to keep the prepared product covered during the application operations				
	The use of BCA01PA is recommended for ISO-Free coating cycles, either stained or not, on any kind of wood substrate				
	As an alternative, for non-fully BCA Iso-free coating cycles it is possible to use LQA6AA1				
	Being exotic woods of different source and variety, it is recommended to make preliminary tests to determine the coating cycle reliability				

WARNINGS

In a coating process with professional products:

- besides the product quality, the final result also depends on numerous other variables, such as environmental conditions; homogeneity in the quality of the support; the constancy of the application cycle; the plants performance; the proper use of the product, etc.
- in the process of industrial coating a certain waste of product is to be considered normal and therefore not attributable to product quality
- The final colour is influenced by the quality and preparation of the support and the conditions of application, for this reason it is essential to check in advance the result in terms of final use

Our Company cannot ensure the control of the coating process carried out by the user. We cannot, therefore, take on any responsibility for the final result achieved through the use of our products. On the other hand, we guarantee the consistency of the chemical and physical characteristics of the product indicated in the relevant Technical Data Sheet, pledging to replace it if it does not correspond to the declared features. Data on the chemical and physical characteristics of the product are recorded at 20°C / 68°F and 70% R.U.

For best results, the optimum conditions of application are:

- Ambient temperature between 18 and 22°C (64 - 72 °F)
- ambient relative humidity between 65 and 70%
- support humidity between 8 and 14%

The conditions to be observed scrupulously are:

- A solvent-based product should be stored indoors at temperatures not below 0 °C / 32°F or above 35 °C / 95°F, in a properly ventilated place, not exposed to solar radiation
- Always shake the products well before use
- Before use, always shake well the product mixed with any other components such as catalysts, accelerators, thinners
- The application must not take place at a temperature lower than 15 °C / 59°F or above 30°C / 86°F
- The drying should not take place at a temperature below 15 °C / 59°F
- The ambient relative humidity during drying should be between 50% and 70%
- To decant paints, exclusively use containers made of suitable material, such as polyethylene and stainless steel
- After use, we recommend that you always close the can carefully

The end result of the coating cycle is the sole responsibility of the users, who must make sure that the product matches their needs and that environmental conditions, application or media specifications do not require substantial changes of use

It is the user's responsibility:

- Adhere to the conditions indicated above
- comply with the rules of hygiene and safety during product application, according to the descriptions given in the safety data sheets
- for solvent-based products spark-proof equipment should be used
- It is forbidden to smoke while using the product

At the bottom of each sheet there is a date of validity

The Company invites you to check with their staff that the product data sheet in your possession is the most updated, since the characteristics of the products are subject to adjustments over time

For more information, please contact (see below):

Issue date: 01/05/2023

Rev.: 3