



Product Data Sheet

Product: **F-260/F-260R**
Description: **Flammable Contact Adhesive**

BENEFITS:

Fast drying
Quick setting
Long Open Time

TYPICAL PHYSICAL PROPERTIES

Base: Synthetic Rubber
Flammability: Highly Flammable
Solids: 28.1%
Density: 6.5 lb/gal
Flash point: -4.0 F
Viscosity: 250 cps
Color: Natural/Red
Coverage Rate: 2.5-3.0 dry grams/sq ft min
Coverage: 165 sq ft/gallon bonded
VOC: 507 g/l (EPA method 24)
Packaging: 5 and 54 gal containers
Clean Up: 689
Shelf Life: 1 Year

Qualifies for LEED®-NC & CI EQ Credit 4.4: laminating adhesives shall contain no urea formaldehyde

SUGGESTED USE:

F-260 is a fast-drying, contact adhesive designed to produce a strong permanent bond in the decorative laminate industry. It can also be used for general purpose applications such as headliners, carpeting & foam fabrication. Its outstanding features include high initial tack, high green strength and long open time.

APPLICATION:

1. It is highly recommended to clean out your spray system prior to switching to this product. It may not be compatible with other cements. This can be accomplished by using a small quantity of our 689 or 822 Cleaner/Thinner thru your pump or pressure pot system. Common solvents to use would be mineral spirits or toluene.
2. Agitate adhesive before use.
3. Substrates should be clean and free of moisture, dirt, oil, and other contaminants.
4. For best results, adhesive and substrates should be allowed to acclimate to room temperature (approximately 60°F or above) before application of adhesive.
5. Apply a minimum of 2.5-3.0 dry grams/sq. ft. For best results, apply two coats of adhesive to any porous surface; one base coat and a secondary top coat. This ensures adequate layup particularly on CARB 2 PARTICLEBOARD and other similar surfaces. Allow the second coat to completely dry before assembly. The adhesive should cover 80% of the surface of the substrate. The coated substrate surface should exhibit a uniform glossy sheen when the adhesive is completely dry. Dull areas indicate insufficient coverage. Adhesive should be re-applied to these areas.
6. 5. Make sure to coat all exposed edges and corners with two coats of adhesives.

FORMICA is a registered trademark of the Formica Corporation

NOTICE TO PURCHASER: The information, data and suggestions for use of the materials given here are based on our best experience and knowledge, but we do not guarantee the results to be obtained in customer's processes. The products discussed are sold without any warranty regarding merchantability or fitness for a particular purpose or any other warranty express or implied. Before using, user shall determine the suitability of the product for his intended use, and user assumes all risk and liability whatsoever in connection therewith. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Sellers and manufacturers only obligation shall be to replace such quantity of the product proved to be defective. Since the manufacturer of the described in this data sheet has no means of controlling the final use of the product by the consumer or user, it is the responsibility of the immediate purchaser and any intermediate sellers to inform the user of the purposes for which the product may be fit and suitable, and of the properties of the product, including the precautionary measures which must be taken in order to insure the safety of the user and of other third persons and property.

55853 X2



666 Redna Terrace, Suite 600
Cincinnati, OH 45215
Customer Service: (800) 330-5566

7. When bonding porous substrates, it is advisable to apply two coats of adhesive. The first coat will act as a sealer and prevent excessive absorption of the adhesive into the substrate. After the first coat has dried, apply a second coat. Allow the second coat to completely dry before assembly.
8. Allowing contact adhesive to dry completely before assembly is essential to obtaining a secure, permanent bond. To check for adhesive dryness, press a piece of Kraft paper onto the adhesive surface. If there is transfer of adhesive to the paper, more time is required to let the adhesive dry. If there is no transfer, substrates are ready for bonding.
9. If areas exist with excessive adhesive deposition, twist the (gloved) fingers while pressing them onto the adhesive layer. This will break any film that has formed as the adhesive dries from the top surface down. If a skin has been formed, allow more time for evaporation to ensure complete removal of solvent before bonding. 8. Dry times can be improved through the use of air movement, drying ovens, lamps, etc.
10. Substrates may be indexed together and bonded once the adhesive is dry. Bonds must be made within the open time of the adhesive. (open times may vary by adhesive).
11. Uniform pressure on the bonded laminates is necessary to create strong, lasting bonds. 40 pounds per linear inch is recommended to insure complete fusion between the two layers of adhesive to be bonded. A pinch roller is ideal for applying uniform pressure. When used properly, a J-roller can also provide adequate pressure for bonding
12. All contact adhesive bonds are immediately able to be routed, trimmed, cut, filed, and machined

SUGGESTED EQUIPMENT:

Product Specifications				
Typical Fluid Pressure		Atomization Pressure		Spray Pattern
10-20 psi		30-50 psi		Web
Spray Equipment				
Binks				
Manual	Auto	Fluid Tip	Needle	Air Cap
95, 2100	21, 95	63ASS	663A, 563A, 263A, 763A	66SD-3
Devilbiss				
Manual	Auto	Fluid Tip & Needle		Air Cap
JGA-510, MBC-510	AGX	FX		247
CA Technologies				
Gun			Set Up	
Panther			1.5 x 2266-3T	
Tomcat			1.5 x 2266-3	

PRECAUTIONS:

Please Refer To The Safety Data Sheet (SDS) For Further Information.

Avoid application equipment containing aluminum or copper.

STORAGE CONDITIONS:

Store between 60 and 90°F. Do not store in direct sunlight

If exposed to freezing temperatures, return product to room temperature.