

# PRODUCT DATA SHEET

## PRODUCT NAME:

PRO BOND YELLOW ASSEMBLY ADHESIVE

## PRODUCT NUMBER:

WUR-BOND-Y

### Typical Physical Properties:

Solids:	43.5% +/- 2.5%
Open Time:	Approx. 5 minutes
Viscosity:	5000 cps
Closed Time:	Approx. 10 minutes
Press Time:	Approx. 30 - 45 minutes @ 40psi
Color:	Yellow
VOC:	3.61 g/l (EPA Method 24)
Coverage:	240 sq ft/gal
Chalk Temperature:	50° F
Coverage Rate:	6 – 9 wet mils
Shelf Life:	1 year in unopened container from date of manufacture
Packaging:	Drums, Pails, Gallons

### Qualifies for LEED®-NC & CI EQ Credit

**4.4: laminating adhesives shall contain no added urea formaldehyde resins**

**3.2: Indoor Air Quality Management plan for the pre-occupancy phase**

**4.1: must be less than current VOC content limits of South Coast Air Quality Management District (SCAQMD) Rule 1168, and all sealants used as fillers must meet or exceed the requirements of the Bay Area Air Quality Management District Regulation 8, Rule 51**

### Properties:

- CAL (SCQAMD) Compliant
- OTC Compliant
- Fast Setting
- Easily Sanded
- No harmful vapors
- Freeze Thaw Stable (3 cycles)
- Low Chalking Temperature

Freezing is not recommended but extensive testing indicates that the glue is freeze thaw stable up to three cycles without any negative impact on performance. If your glue has been frozen, allow it acclimate to room temperature and shake/stir to original form.

### Application:

**General Assembly:** Insure the bondline is smooth and free of any dirt, dust or contaminant. Apply by squeeze bottle, hand roller or glue spreader thoroughly over the surface to be bonded. Snugly fit the parts together and apply pressure by clamping or other pressure source with a minimum of 100 psi. There should be a small amount of squeeze out along the edges.

### Applications to Avoid:

Moisture Resistant Board  
Fire retardant treated board materials  
Metallic, polyester or painted surfaces  
Low pressure melamine surfaces  
Tempered hardboard surfaces

### Limitations:

Not intended for exterior use or where moisture is likely. For exterior applications use Type II Assembly Adhesive. Not for structural or load bearing applications. Do not use when temperature, glue or materials are below 50°F. Freezing may not affect the function of the product but may cause it to thicken. Agitation should restore product to original form.

### General Use Instructions:

Substrates and adhesive should be conditioned to 65° F prior to use  
Substrates to be bonded must be clean, free of dust and any other contaminants

### Clean Up:

Use warm soapy water when the adhesive is wet and solvent or diluted ammonia when the adhesive is dry.  
Wash water is considered RCRA non hazardous  
Dispose of waste in accordance with regulations.

**Application Precautions:**

Moisture Resistant Board  
Fire retardant treated board materials  
Metallic, polyester or painted surfaces  
Low pressure melamine surfaces  
Tempered hardboard surfaces.

**Storage Conditions:**

Rotate stock, use oldest first.

Thinning is not recommended or required. However, should the adhesive become too thick, use water to thin.

Use water for cleanup.

Keep adhesive container closed tightly when not in use. Store closed, lined containers where temperature will not be less than 50°F (10°C) and should not exceed 90°F (32°C).

DO NOT ALLOW PRODUCT TO FREEZE

Product should not be stored in direct sunlight

**Please Refer To The Safety Data Sheet For Further Information.**

Art. No

Natural/Clear  
0893100838088  
0893100839088  
0893100840088